

3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 134

Product Description

3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 134 is a one-part, heat curable, thermosetting epoxy coating designed for corrosion protection of metal. The epoxy is applied to preheated steel as a dry powder which melts and cures to a uniform coating thickness. This bonding process provides excellent adhesion and coverage on applications such as valves, pumps, pipe drains, hydrants and porous castings. Scotchkote 134 coating is resistant to wastewater, corrosive soils, hydrocarbons, harsh chemicals, and sea water. Powder properties allow easy manual or automatic application by electrostatic or air-spray equipment.

Product Features

- No primer required for most applications.
- Particularly suitable for electrostatic or air-spray application on preheated metal articles.
- Can be electrostatically applied to unheated metal parts and subsequently cured by baking.
- Long gel time allows application on large or complex articles, minimizing fear of runs, sags, laminations, or unsightly overspray.
- Especially useful for coating the inside of pipe or other fabrications where a smooth, corrosion resistant coating is required.
- Can be machined by grinding or cutting to meet close tolerance requirements.
- Allows easy visual inspection of coated articles.
- Can be painted with alkyd paint, acrylic lacquer, polyurethane, or acrylic enamel for color coding.
- Will not sag, cold flow, or become soft in storage. Long term storage under most climatic conditions.
- Lightweight for lower shipping costs.
- Protects over wide temperature range.
- Resists direct burial soil stress.
- High adhesion and toughness.
- Resists cavitation and cathodic disbondment.
- Excellent chemical resistance.

- Suitable for elevated temperature service in presence of H₂S, CO₂, CH₄, crude oil and brine when applied over phenolic primer such as Scotchkote 345.
- Long-term performance history in water, sewage, and other service environments.
- Scotchkote 134 coating has been tested and certified to NSF /ANSI Standard 61, Drinking Water System Components. For NSF certified applications, max approved thickness is 60 mil (1.5 mm). 
- Scotchkote 134 FBEC meets the requirements of AWWA Standard C213 and C550.
- Operating temperature dry is 235°F/ 113°C and wet is 175°F/79°C.

General Application Information

1. Remove oil, grease and loosely adhering deposits.
2. Abrasive blast clean the surface to NACE No. 2/SSPC-SP10 ISO 8501:1, Grade SA 2 1/2 near-white metal.
3. Apply mechanical masks or mask with materials such as Scotch Glass Cloth Tape 361 or Scotch Aluminum Foil Tape 425 as required.
4. Preheat article to the desired application temperature per cure specifications.
5. Deposit Scotchkote 134 coating by powder spray to the specified thickness.
6. Cure according to cure specifications.
7. Visually and electrically inspect for coating flaws after the coating has cooled.
8. Repair all defects.

Cure Specifications

Scotchkote 134 coating may be applied to metal articles which have been preheated to a temperature of 300°F/149°C to 475°F/246°C. After application, Scotchkote 134 coating must be cured according to the cure guide to achieve maximum performance properties.

If Scotchkote 134 coating is electrostatically applied to unheated parts, the cure time should be measured from the time the coated part reaches the cure temperature. After cure, the coating may be force cooled using air or water to facilitate inspection and handling.



3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 134 Cure Guide

Temperature of Article at Time of Powder Application	Typical Gel Time	Cure Time
475°F/246°C	40 seconds	7 minutes
450°F/232°C	60 seconds	10 minutes
400°F/204°C	120 seconds	15 minutes
350°F/177°C	330 seconds	25 minutes
425°F/218°C	90 seconds	25 minutes for NSF/ANSI 61 approved applications

Typical Properties

Property	Value
Color	Forest Green
Specific Gravity - Powder (Air Pycnometer)	1.51
Coverage	127 ft ² /lb/mil (0,66 m ² /kg/mm)
Fluid Bed Density	33 lbs/ft ³ (530 kg/m ³)
Shelf Life at 80°F/27°C	18 months
Average Gel Time 400°F/204°C	120 seconds
Edge Coverage	12% to 18%
Minimum Explosive Concentration	0.03 oz/ft ³ (30,6 g/m ³)
Ignition Temperature	986°F/530°C
V.O.C. (As Supplied)	0 g/L, as calculated

Chemical/Pressure/Temperature Resistance

All tests performed on Scotchkote™ Fusion Bonded Epoxy Coating 134 applied over a 1 mil/25,4 µm phenolic primer. Liquid phase for all test conditions: 33% kerosene, 33% toluene, 34% brine solution of 5% NaCl.

Test Conditions	Gas Phase	Results
Autoclave, 120°F/49°C 48 hours, 1500 psi/10.3 MPa	99.5% CO ₂ 0.5% H ₂ S	Excellent adhesion, no coating loss or blisters in aqueous, hydrocarbon, or gas phase
Autoclave, 150°F/66°C 48 hours, 2200 psi/15.2 MPa	80% CH ₄ 12% CO ₂ 8% H ₂ S	Excellent adhesion, no coating loss or blisters in aqueous, hydrocarbon, or gas phase
Autoclave, 200°F/93°C 24 hours, 3300 psi/22.8 MPa	86% CH ₄ 8% CO ₂ 6% H ₂ S	Excellent adhesion, no coating loss or blisters in aqueous, hydrocarbon, or gas phase
Autoclave, 300°F/149°C 24 hours, 3000 psi/20.7 MPa	90% CH ₄ 10% CO ₂ Trace H ₂ S	Excellent adhesion, no coating loss or blisters in aqueous, hydrocarbon, or gas phase

3M™ Scotchkote Fusion-Bonded Epoxy Coating 134 Test Data

Property	Test Description	Results
Adhesion	Elcometer	> 3000 psi (glue failure)/ 210 kg/cm ²
Adhesion to Steel (Shear)	ASTM D 1002 10 mil/254 µm glue line	4300 psi/302 kg/cm ² cohesive failure
Impact	Gardner 5/8 in/1,6 cm diameter tup 1/8" x 3" x 3" (0,32 cm x 7,6 cm x 7,6 cm) steel panel	160 in-lbs 1,8 kg•m
Hardness	Barcol ASTM D 2583	23
Abrasion Resistance	ASTM D 4060 CS-17 1000g weight / 5000 cycles	0,07 g loss
Thermal Shock	310°F/154°C to -320°F/-195°C coated pipe	10 cycles, no effect
Penetration	ASTM G 17 -40°F/-40°C to 240°F/116°C	0
Tensile Strength	ASTM D 2370	7300 psi/512 kg/cm ²
Elongation	ASTM D 2370	4.2%
Compressive Strength	ASTM D 695	12800 psi/900 kg/cm ²
Coefficient of Friction	API RP5L2-1968, App 8	23°
Electric Strength	ASTM D 149	1000 volts/mil (39,4 kv/mm)
Hot Water Resistance	160°F/71°C immersion / 120 days	Good adhesion, no blistering
Electrical Resistivity	ASTM D 257	1.2 x 10 ¹⁵ ohm•cm
Thermal Conductivity	MIL-I-16923E	7 x 10 ⁻⁴ cal/sec/cm ² /°C/cm
Water Absorption	3M 10 mil/254 µm free film 30 days	6,5 g/m ²
Fungus Resistance	MIL-STD 810-B Method 508	Funginert
Salt Fog	MIL-E-5272C	No effect
Weatherometer	ASTM G 23 5000 hours	Surface chalk
Soil Stress - Burial	Bureau of Reclamation 25 cycles	No effect
Salt Crock	30 day, 5 volt, 5% NaCl sand crock 230°F/110°C	Disbondment diameter 24 mm average
Bendability	3/8"/9,5 mm coupon mandrel bend at 73°F/23°C	30 pipe diameters 1.9° / diameter length

Handling and Safety Precautions

Read all Health Hazard, Precautionary and First Aid, Material Safety Data Sheet, and/or product label prior to handling or use.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.



Infrastructure Protection Division

6801 River Place Blvd.
Austin, TX 78726-9000
www.3M.com/corrosion

Please recycle. Printed in USA.
© 3M 2012. All rights reserved.
80-6111-8506-9 Rev. A

Ordering Information/Customer Service

For ordering technical or product information, or a copy of the Material Safety Data Sheet, call:
Phone: 800/722-6721
Fax: 877/601-1305

Warranty; Limited Remedy; Limited Liability.

Because conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties: this product will conform to 3M's published product specifications and be free from defects in material and manufacture on the date of your purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective upon your receipt, your exclusive remedy shall be, at 3M's option, to replace the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**